

# FUSION FIX GP

## Key Features

- Easy to use
- Temporary spray adhesive
- Compatible with all resins
- 20 minute tack time
- Doesn't effect laminate strength

## Product Description

FusionFix™ GP is a high performance spray adhesive designed specifically for temporary positioning of fibre reinforcements, core materials, fixings and bagging consumables during resin infusion and other composites laminating processes.

Unlike conventional spray adhesives, FusionFix™ GP has been developed to be compatible with all resin systems including epoxy, vinylester and polyester resin systems. Even in the case of over-application, FusionFix™ GP will not reduce the interlaminar shear strength of composite laminates.

## Recommended Uses

FusionFix has been developed specifically for the temporary fixing of fibres reinforcements patches and core product of any material, as well as environmental products, during the laying up stage of the Resin Infusion process.

FusionFix has been tested and found to be compatible with a wide range of resin systems, including our own IN2 Epoxy Infusion and IP2 Polyester Infusion resins, however you should always conduct your own tests to ensure compatibility.

**IMPORTANT:** Although a very light application of FusionFix GP is almost undetectable, the product is NOT intended for use as a spray adhesive for unpainted, natural finish cosmetic carbon fibre parts. It is NOT completely transparent and will be visible when used to hold reinforcement directly onto a mould surface.

## How to Use

Thoroughly shake the can before use. After use, clean the nozzle through by turning the can upside down and spraying briefly.

Apply sparingly, ensuring that you use the least adhesive necessary. Be particularly sparing when spraying directly onto the mould surface to position visible surface layers of reinforcement; a light misting from a distance of 30cm should be sufficient.

For positioning of heavier reinforcements and core materials the adhesive

can be applied to one or both surfaces at a coverage of around 30g/m<sup>2</sup>. The adhesive remains tacky for up to 20 minutes but is most tacky after around 2 minutes once the solvent carrier evaporates.

Before clear-coating or painting parts, use alcohol to remove adhesive traces from the surface of the parts..

## Transport and Storage

Resin and hardener should be kept in tightly seal containers during transport and storage. Both the resin and hardener should be stored in ambient conditions of between 10°C (50°F) and 25°C (77°F).

When stored correctly, the resin and hardener will have a shelf-life of 12 months. Although it may be possible to use the resin after a longer period, a deterioration in the performance of the resin will occur, especially in relation to clarity and cure profile.

Pay particular attention to ensuring that containers are kept tightly sealed. Epoxy hardeners especially will deteriorate quickly when exposed to air.

## Disclaimer

This data is not to be used for specifications. Values listed are for typical properties and should not be considered minimum or maximum.

Our technical advice, whether verbal or in writing, is given in good faith but Easy Composites Ltd gives no warranty; express or implied, and all products are sold upon condition that purchasers will make their own tests to determine the quality and suitability of the product for their particular application and circumstances.

Easy Composites Ltd shall be in no way responsible for the proper use and service of the product, nor for the safeguarding of personnel or property, all of which is the duty of the user. Any information or suggestions are without warranty of any kind and purchasers are solely responsible for any loss arising from the use of such information or suggestions. No information or suggestions given by us shall be deemed to be a recommendation to use any product in conflict with any existing patent rights. Before using any of our products, users should familiarise themselves with the relevant technical and safety datasheets provided by Easy Composites Ltd.